

SOLDER CONNECTION

Email: sales@solderconnection.co.uk | Tel: +44(0)1291 624 400

QUALITEK® Technical Bulletin

Delta DSP 230 62/36/2 Rosin Mildly Activated Solder Paste

DESCRIPTION

Delta DSP 230 Sn62/Pb36/Ag2 Solder Paste is a non-corrosive and a mildly activated rosin solder paste designed for surface mount assembly applications with excellent printing properties, including fine pitch. DSP 230 is available with tin/lead, tin/lead/silver and lead-free alloys. The post soldering residues of DSP 230 are non-conductive, non-corrosive and highly insulated.

FEATURES AND BENEFITS

- Excellent wettability
- Yields bright shiny joints
- Designed for fine pitch printing
- Available with both leaded and lead-free alloys

TECHNICAL DATA

	Specification	Test Method
Flux Classification	ROLO	IPC-J-STD-004B
Copper Mirror	No removal of copper film	IPC-TM-650 2.3.32
Corrosion	Pass	IPC-TM-650 2.6.15
SIR	>1.0 x 10 ⁸ ohms	IPC-TM-650 2.6.3.3
Post Reflow Flux Residue	55%	TGA Analysis
Metal Loading	90%	IPC-TM-650 2.2.20
Viscosity		
Malcom ⁽²⁾ , poise	1750-2050	IPC-TM-650 2.4.34.3 modified
Thixotropic Index	0.50-0.60	
Slump Test	Pass	IPC-TM-650 2.4.35
Solder Ball Test	Pass	IPC-TM-650 2.4.43
Tack		
Initial	112gm	JIS Z 3284
Tack retention @ 24 hr	98gm	JIS Z 3284
Stencil Life	>4hrs	QIT 3.44.5
Abandon Time	30 min	QIT 3.44.6

PARTICLE SIZE

Sn62/Pb36/Ag2 alloy is available in Type 3(45-25m), 4(38-20µm) and 5 (25-15µm) IPC-J-STD-005A powder distribution. Solder powder distribution is measured utilizing laser diffraction, optical analysis and sieve analysis. Careful control of solder powder manufacturing processes ensures the particles' shape are 95% spherical minimum (aspect ratio < 1.5) and that the alloy contains a typical maximum oxide level of 80 ppm.


SOLDER COMPOSITION

Sn62 alloy is the conventional non-eutectic solder used in most electronic assemblies. The Sn62 alloy conforms and exceeds the impurity requirements of IPC-J-STD-006C and all other relevant international standards.

TYPICAL ANALYSIS

Sn	Pb	Ag	Al	As	Au	Bi	Cd	Cu	Fe	In	Ni	Sb	Zn
61.5 -62.5	Bal	1.8 - 2.2	0.005 Max	0.030 Max	0.050 Max	0.100 Max	0.002 Max	0.080 Max	0.020 Max	0.100 Max	0.010 Max	0.200 Max	0.003 Max

Issue 2 - 07/09/22



SOLDER CONNECTION

Email: sales@solderconnection.co.uk | Tel: +44(0)1291 624 400

	Sn62/Pb36/Ag2
Melting Point, °C	179 - 189
Hardness, Brinell	14 HB
Coefficient of Thermal Expansion	27.0
Tensile Strength, psi	4442
Density, g/cc	8.50
Electrical Resistivity, (μohm-cm)	14.5
Electrical Conductivity, 10 ⁴ /ohm-cm	6.9

	Sn62/Pb36/Ag2
Yield Strength, psi	3950
Total Elongation, %	48
Joint Shear Strength, at 0.1mm/min 20 °C	37.0
Joint Shear Strength, at 0.1mm/min 100 °C	16.2
Creep Strength, N/mm ² at 0.1mm/min 20 °C	3.3
Creep Strength, N/mm ² at 0.1mm/min 100 °C	1
Thermal Conductivity, W/mK	50.9

METAL LOADING

Typical metal loading for stencil printing application of R.M.A. 230 paste with lead-containing alloys is 89.0-90.0 %.

PRINTING OF SOLDER PASTE

Stencil:

Use of chemical etched/electroformed stencil is preferred, however, Sn62/62/36/2 DSP 230 has been used successfully with chemical etch, electroformed, and laser cut stencils.

Squeegee:

Blades: Metal (stainless steel) squeegee blades angled from 45-60° give the best print definition. Metal (nickel) squeegee blades angled from 45-60° give the best performance. 90 durometer polyurethane may also be used.

Pressure: Pressure should be adjusted at the point where the paste leaves a relatively clean stencil after each print pass. Typical pressure setting 0.6-1.5lb per linear inch of blade.

Speed: Normal print speeds are 1.0-2.5 (25-50mm) per second. As print speeds increase pressure will need to be increased. Although slower print speeds are desirable, Delta solder paste is capable of printing up to 6 inch per second.

PRINT DEFINITION

62/36/2 DSP 230 provides excellent print definition characterized by brick-like prints. Good release is seen on 12-9 mil apertures with prints speeds in the range of 1.0-6.0 inch per second (25mm-150mm).

APPLICATION


Solder paste should be taken out of the refrigerator at least 3 to 6 hours prior to use. This will give the paste enough time to come to thermal equilibrium with the environment. Also, any fresh jar of solder paste should be gently mixed for at least one minute with a spatula. Be sure not to mix the paste too vigorously, as this will degrade the paste's viscosity characteristics and introduce entrapped air into the paste. The purpose of the mixing is to insure that the paste is smooth and consistent. If solder paste is supplied in cartridges pre-mixing is not necessary due to the shear action produced from the dispensing.

OPEN & ABANDON TIME

Tests have proven that DSP 230 will perform during continuous printing for up to 8 hrs. Field test have shown that an abandon time of at least 1 hr is possible, resulting in a perfect 1st pass print on resumption of printing.

WORKING ENVIRONMENT

Solder paste performs best when used in a controlled environment. Maintaining ambient temperature between 68-77 °F (20-25 °C) at a relative humidity of 40-65% will ensure consistent performance and maximum life of paste.




SOLDER CONNECTION

Email: sales@solderconnection.co.uk | Tel: +44(0)1291 624 400

REFLOW

Best results have been achieved when 62/36/2 DSP 230 is reflowed in a forced air convection oven with a minimum of 8 zones (top & bottom), however, reflow is possible with a 4 zone oven (top & bottom).

The following is a recommended profile for a forced air convection reflow process. The melting temperature of the solder, the heat resistance of the components, and the characteristics of the PCB (i.e. density, thickness, etc.) determine the actual reflow profile.



Preheat Zone- The preheat zone, is also referred to as the ramp zone, and is used to elevate the temperature of the PCB to the desired soak temperature. In the preheat zone the temperature of the PCB is constantly rising, at a rate that should not exceed 2.5 C/sec. The oven's preheat zone should normally occupy 25-33% of the total heated tunnel length.

The Soak Zone- normally occupies 33-50% of the total heated tunnel length exposes the PCB to a relatively steady temperature that will allow the components of different mass to be uniform in temperature. The soak zone also allows the flux to concentrate and the volatiles to escape from the paste.

The Reflow Zone- or spike zone is to elevate the temperature of the PCB assembly from the activation temperature to the recommended peak temperature. The activation temperature is always somewhat below the melting point of the alloy, while the peak temperature is always above the melting point.

FLUX RESIDUES & CLEANING

DSP 230 is an R.M.A. formulation therefore the residues should be removed for typical applications. If residue removal is desired, the use of Everkleen 1005 Buffered Saponifier with a 5-15% concentration in hot 60 °C (140 °F) will aid in residue removal.

STORAGE & SHELF LIFE

It is recommended that solder paste be stored at a temperature of between 35-50 °F (2-10 °C) to minimize solvent evaporation, flux separation, and chemical activity. If room temperature storage is necessary, maintain temperatures between 68-77 °F (20-25 °C). Shelf life is 6 months from date of manufacture.

STENCIL CLEANING

Periodic cleaning of the stencil during production is recommended to prevent any paste from being deposited in unwanted areas of the board and to eliminate solder balling.

DISPOSAL

62/36/2 DSP 230 should be stored in a sealed container and disposed of in accordance with federal, state and local authority requirements.

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of the materials designated.